

TECHNICAL INFORMATION SERIE SPU

Application

Suitable for printing onto variety of nylon fabrics such as umbrellas, sports bags, etc.

Aspect

Gloss

Drying

30-60 minutes in open air, immediate drying in tunnel (2 minutes).

Thinning

SPU 2000 – NORMAL REDUCER
SPU 8000 – SLOW REDUCER.
Average reducer quantity: +/-15%

Cleaning

Cleaner TS 2000.

Films

All films are suited.

Covering capacity

12 to 16 m² per Kg, depending on the used screen.

Storage stability

Several years.

Colours

All colours available.
High opacity

Resistance to light and weather conditions

Good weather resistant

Resistance to washing conditions

Excellent wash conditions

Mesh

P77-90 Monofilament
P43-80 Polyester Mesh

Emulsion

All solvent resistant films are suited.

Complementary products

Good adherence after addition of +/-10% HPU catalyst. the mixture is only 24 hours tenable. And must be tested on the material.

Important :

Stir well before use.

Always make a proof before you start the final work.

